

徳島 構造体強度補正カレンダー (高炉セメントB種)

阿南生コンクリート工業株式会社
 徳島県阿南市宝田町平岡898番地
 TEL (0884) 22-2020 FAX (0884) 22-0398

1月	月平均気温 (6.3°C)	(日)	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31
	日平均気温	(°C)	7.1	7.0	7.0	6.9	6.9	6.8	6.8	6.7	6.7	6.6	6.6	6.5	6.5	6.4	6.3	6.3	6.2	6.2	6.1	6.1	6.0	6.0	5.9	5.9	5.9	5.8	5.8	5.8	5.8	5.8	5.8
	材齢28日までの平均気温	(°C)	6.3	6.3	6.3	6.2	6.2	6.2	6.1	6.1	6.1	6.1	6.0	6.0	6.0	6.0	6.0	6.1	6.1	6.1	6.1	6.1	6.1	6.2	6.2	6.3	6.3	6.4	6.4	6.5	6.6	6.6	6.7
2月	月平均気温 (6.8°C)	(日)	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29		
	日平均気温	(°C)	5.9	5.9	5.9	6.0	6.0	6.1	6.1	6.2	6.3	6.4	6.5	6.5	6.6	6.7	6.7	6.8	6.9	7.0	7.1	7.2	7.3	7.4	7.5	7.6	7.8	7.9	8.0	8.1	8.2		
	材齢28日までの平均気温	(°C)	6.9	7.0	7.1	7.1	7.2	7.3	7.4	7.5	7.6	7.7	7.8	7.9	8.0	8.1	8.2	8.3	8.4	8.5	8.6	8.7	8.8	8.9	9.1	9.2	9.3	9.4	9.5	9.6	9.7		
3月	月平均気温 (9.9°C)	(日)	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31
	日平均気温	(°C)	8.2	8.3	8.4	8.5	8.6	8.7	8.8	8.9	9.0	9.1	9.2	9.3	9.4	9.6	9.7	9.9	10.0	10.2	10.3	10.4	10.6	10.7	10.8	10.9	11.1	11.2	11.4	11.6	11.7	11.9	12.1
	材齢28日までの平均気温	(°C)	9.9	10.0	10.1	10.3	10.4	10.5	10.7	10.8	11.0	11.2	11.3	11.5	11.6	11.8	12.0	12.2	12.3	12.5	12.7	12.9	13.0	13.2	13.4	13.6	13.7	13.9	14.1	14.3	14.5	14.6	14.8
4月	月平均気温 (15.0°C)	(日)	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	
	日平均気温	(°C)	12.3	12.5	12.7	12.9	13.1	13.3	13.5	13.7	13.9	14.1	14.3	14.5	14.6	14.8	15.0	15.2	15.4	15.5	15.7	15.8	16.0	16.1	16.3	16.4	16.6	16.8	16.9	17.1	17.3	17.5	
	材齢28日までの平均気温	(°C)	15.0	15.2	15.4	15.5	15.7	15.9	16.1	16.2	16.4	16.6	16.7	16.9	17.0	17.2	17.3	17.5	17.6	17.8	17.9	18.0	18.2	18.3	18.4	18.6	18.7	18.9	19.0	19.1	19.2	19.4	
5月	月平均気温 (19.6°C)	(日)	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31
	日平均気温	(°C)	17.7	17.8	18.0	18.3	18.3	18.5	18.6	18.7	18.8	18.9	18.9	19.0	19.1	19.2	19.3	19.5	19.6	19.7	19.9	20.0	20.1	20.3	20.4	20.5	20.6	20.8	20.9	21.0	21.1	21.2	21.3
	材齢28日までの平均気温	(°C)	19.5	19.6	19.7	19.8	20.0	20.1	20.2	20.3	20.4	20.5	20.6	20.8	20.9	21.0	21.1	21.2	21.3	21.4	21.6	21.7	21.8	21.9	22.0	22.1	22.2	22.3	22.4	22.5	22.6	22.7	22.8
6月	月平均気温 (23.0°C)	(日)	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	
	日平均気温	(°C)	21.4	21.5	21.6	21.7	21.8	21.9	22.1	22.2	22.3	22.4	22.5	22.6	22.7	22.8	22.9	23.0	23.0	23.1	23.2	23.3	23.4	23.6	23.7	23.9	24.0	24.2	24.3	24.5	24.6	24.8	
	材齢28日までの平均気温	(°C)	26.7	23.1	23.2	23.3	23.4	23.6	23.7	23.8	23.9	24.1	24.2	24.3	24.4	24.6	24.7	24.8	25.0	25.1	25.2	25.4	25.5	25.7	25.8	25.9	26.1	26.2	26.3	26.4	26.6	26.7	
7月	月平均気温 (26.8°C)	(日)	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31
	日平均気温	(°C)	24.9	25.1	25.2	25.4	25.5	25.6	25.8	25.9	26.0	26.2	26.3	26.5	26.6	26.7	26.8	26.9	27.0	27.2	27.3	27.4	27.5	27.6	27.7	27.8	27.9	27.9	28.0	28.1	28.2	28.2	28.3
	材齢28日までの平均気温	(°C)	26.8	26.9	27.0	27.1	27.2	27.3	27.4	27.5	27.6	27.7	27.8	27.8	27.9	28.0	28.0	28.1	28.1	28.2	28.2	28.2	28.2	28.3	28.3	28.3	28.3	28.3	28.3	28.3	28.2	28.2	28.2
8月	月平均気温 (28.1°C)	(日)	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31
	日平均気温	(°C)	28.3	28.4	28.4	28.4	28.5	28.5	28.5	28.5	28.5	28.5	28.5	28.4	28.4	28.4	28.3	28.3	28.2	28.2	28.1	28.0	28.0	27.9	27.8	27.7	27.6	27.5	27.4	27.3	27.2	27.1	27.0
	材齢28日までの平均気温	(°C)	28.1	28.1	28.0	28.0	27.9	27.8	27.8	27.7	27.6	27.5	27.5	27.4	27.3	27.2	27.1	27.0	26.9	26.8	26.6	26.5	26.4	26.3	26.1	26.0	25.8	25.7	25.5	25.4	25.2	25.1	24.9
9月	月平均気温 (24.8°C)	(日)	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	
	日平均気温	(°C)	26.9	26.8	26.7	26.6	26.5	26.3	26.2	26.1	25.9	25.8	25.7	25.5	25.3	25.2	25.0	24.8	24.6	24.4	24.2	24.0	23.8	23.6	23.4	23.2	23.1	22.9	22.7	22.5	22.4	22.2	
	材齢28日までの平均気温	(°C)	24.8	24.6	24.4	24.3	24.1	23.9	23.7	23.6	23.4	23.2	23.0	22.9	22.7	22.5	22.3	22.2	22.0	21.8	21.6	21.4	21.2	21.1	20.9	20.7	20.5	20.3	20.2	20.0	19.8	19.6	
10月	月平均気温 (19.3°C)	(日)	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31
	日平均気温	(°C)	22.0	21.9	21.7	21.6	21.4	21.2	21.0	20.9	20.7	20.5	20.3	20.2	20.0	19.8	19.6	19.3	19.1	18.9	18.7	18.5	18.4	18.2	18.0	17.8	17.6	17.4	17.2	17.0	16.8	16.6	16.5
	材齢28日までの平均気温	(°C)	19.4	19.2	19.0	18.9	18.7	18.5	18.3	18.1	17.9	17.7	17.6	17.4	17.2	17.0	16.8	16.7	16.5	16.3	16.1	15.9	15.8	15.6	15.4	15.2	15.0	14.8	14.6	14.5	14.3	14.1	13.9
11月	月平均気温 (13.8°C)	(日)	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	
	日平均気温	(°C)	16.3	16.1	16.0	15.9	15.7	15.6	15.4	15.3	15.1	14.9	14.7	14.5	14.3	14.1	13.8	13.6	13.4	13.2	13.0	12.8	12.6	12.4	12.3	12.1	12.0	11.9	11.7	11.6	11.4	11.2	
	材齢28日までの平均気温	(°C)	13.8	13.6	13.4	13.2	13.1	12.9	12.7	12.5	12.3	12.1	11.9	11.7	11.6	11.4	11.2	11.0	10.8	10.7	10.5	10.3	10.2	10.0	9.9	9.7	9.6	9.4	9.3	9.1	9.0	8.9	
12月	月平均気温 (8.7°C)	(日)	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31
	日平均気温	(°C)	11.1	10.9	10.7	10.5	10.2	10.0	9.8	9.6	9.4	9.2	9.1	8.9	8.8	8.6	8.5	8.4	8.3	8.2	8.2	8.1	8.0	7.9	7.9	7.8	7.7	7.6	7.5	7.4	7.3	7.2	7.1
	材齢28日までの平均気温	(°C)	8.7	8.6	8.5	8.4	8.2	8.1	8.0	7.9	7.8	7.8	7.7	7.6	7.5	7.4	7.4	7.3	7.2	7.2	7.1	7.0	7.0	6.9	6.8	6.8	6.7	6.6	6.6	6.5	6.5	6.4	6.4

表示区分	色別による区分 構造体強度補正		適 応 期 間		参 照 資 料		備 考 欄
		3 N/mm ²	3/21~7/1 9/15~11/5	当区分に基づく上表の適応期間は、主たる仕様書による高炉セメントB種を使用した時の標準を示す。		建築工事標準仕様書 JASS 5 (日本建築学会)	
	6 N/mm ²	7/2~9/14 11/6~3/20	公共建築工事標準仕様書 (公共建築協会)				

暑中期間における構造体強度補正值 28S91は(6N/mm²) 適用期間は日平均気温の平年値が25°Cを超える期間を標準とする。